

## SD Powder Coating

---

### Product Description

SD series powder coatings are mainly made of super durable polyester resin, curing agent and pigment, which are suitable for high level architectural decoration and protection for at least 15 years application. It has been certified to meet the requirement of Qualicoat Class 2.

---

### Film Appearance & Package

Appearance effects: smooth surface (all kinds of gloss range), sanding, hammer effect

Color: Most of RAL colors or according to requirement

Packing: 20Kgs. Carton boxes with double PE-bag.

For more information, please contact us.

---

### Physical Data

Specific gravity: 1.2-1.7 (depending on the gloss and color)

Dry flow ability: 120-160

Particle size: 100% < 160µm, according to requirement

---

### Substrate & Preparation

Substrate: 1-Aluminum profile and aluminum sheet. 2-Steel or galvanized steel sheet. 3-Also can be used to protect and decorate indoor equipment (For more information, please contact us).

Preparation: To achieve the best performance of SD series products, the pretreatment must be carried out according to the construction guidelines. The base material shall be pre-treated according to GB/T 9271 or ISO 1514. The cold-rolled steel plate tested for salt spray resistance shall be phosphate in addition to GB/T 9271. If the product is applied in high-anticorrosive environment of C4 or above (rated according to ISO12944), it can be used with Huajia anticorrosive special primer (please consult us).

---

### Curing Condition (Object Temperature)

-> Can be used such as IR, gas, hot convection drying path, oven and other ways of curing.

-> If use the gas oven to bake, combustion by-products will change the color of the film.

Recommended curing condition: Object temperature/time 200-210°C/10-15min

---

### Application

- Do not mix this product with others
- The substrate must be properly pre-treated before powder application
- Manual or automatic electrostatic spraying can be used
- The film thickness should be determined according to the geometry and requirement of the coated object, and the performance should be evaluated when the film thickness is less than 60µm

---

黄山华佳表面科技有限公司

中国, 安徽省, 黄山市, 徽州区, 永佳大道 109#

电话: 0086 559-3515170 传真: 0086 559-3511660

网站: [www.hjchem.com](http://www.hjchem.com)

Huangshan Huajia Surface Technology Co., Ltd

No. 109 Yongjia Ave., Huizhou Dist, Huangshan City, Anhui, PRC

Tel: 0086 559-3515170 Fax: 0086 559-3511660

[www.hjchem.com](http://www.hjchem.com)

## SD Powder Coating

### Product Performance & Film Properties

PROPERTIES	TEST METHOD	CRITERIA
Film Thickness	ISO 2360	60-80um
Adhesion	ISO 2409	Class 0
Hardness	ISO 2815	≥80
Cupping Test	ISO 1520	≥5mm
Bend Test	ISO 1519	≤3mm
Salt Spray	ISO 9227	Aluminum Substrate: Acetic acid salt spray 1000h – no corrosion area more than 4mm from scribe
		Other Substrates: salt spray 500h - no corrosion area more than 2mm from scribe
Impact Test	ISO 6272	≥2.5Nm
	GB/T 1732	50cm*Kg
Humidity	ISO 6270	Pass at 1000 hours – no corrosion area ≤2 mm from scribe
Accelerated Weathering Test	ISO 11341	1000h Q-Sun test ≥ 90% Gloss retention, ΔE according to Qualicoat requirement (appendix A7)
Florida Test	ISO 2810	3-year Florida exposure, ≥ 50% Gloss retention, ΔE according to Qualicoat requirement (appendix A7)

Note: 1-All chemical and physical properties are laboratory test results (unless otherwise stated), and are for reference only in application. The performance still needs to depend on the final use environment of the product.  
2-The substrate for the above chemical and physical tests is chromate aluminum plate, and all test plates are sprayed with a film thickness of 60 to 80 μm .

### Storage Stability

Store in a cool ( $\leq 25^{\circ}\text{C}$ ), dry warehouse, prevent direct sunlight, and should be isolated from fire source, away from heat source. Storage life is 6 months from the date of production.

### Safety Precaution

All dusts are respiratory irritants. Therefore, inhalation of the dust or of the vapour resulting from the cure should be avoided. Take step to prevent skin contact, but should contact occur, wash skin with soap and water. In case of eye contact flush immediately with clean water and seek medical advice. Dust and powder should not be allowed to build up on surface or ledge. Dust clouds of any finely divided organic material can be ignited with an electric spark or open flame. All equipment should be electrically earthed to prevent build up of static.

黄山华佳表面科技有限公司

中国, 安徽省, 黄山市, 徽州区, 永佳大道 109#

电话: 0086 559-3515170 传真: 0086 559-3511660

网站: [www.hjchem.com](http://www.hjchem.com)

Huangshan Huajia Surface Technology Co., Ltd

No. 109 Yongjia Ave., Huizhou Dist, Huangshan City, Anhui, PRC

Tel: 0086 559-3515170 Fax: 0086 559-3511660

[www.hjchem.com](http://www.hjchem.com)